

S-394-MG

Micronized Wax

Shamrock's product line of micronized waxes provide rub and abrasion resistance. Included in this line are products that provide gloss, matting, clarity, and controlled slip in a range of particle sizes.

Product Description:

S-394-MG is a synthetic wax with a DSC melt peak above 110°C.







Application:

S-394-MG is recommended for liquid and paste inks. S-394-MG is also recommended for use in many types of coating systems including solvent-based, water-based, UV, and powder coatings. S-394-MG can be used for both pigmented and clear compositions. S-394-MG is recommended at 2-3% of total formula weight for slip and abrasion resistance and 5-10% for matting.

Features and Benefits:

-  Good Abrasion Resistance
-  Good Slip
-  Assists in Matting

Typical Properties:

	Specific Gravity:	0.95 g/cm ³
	Particle Size Mean Value:	5 µm
	99% of Particle Under:	12 µm
	NPIRI Grind:	2.5 max
	Hegman Grind:	6.5 min
	Melting Point:	230/110 °F/°C

Regulatory Status:

The components of this product are listed on multiple chemical inventories. For specific information on the applicable chemical inventories, please refer to the product SDS. This product meets the requirements of 21 CFR 175.105, 175.250, 175.300, 175.320, 176.170, and 176.180.

Safety, Shipping and Handling:

For complete safety, shipping and handling information please contact your regional Customer Service Representative, or our Customer Service Team at customerserviceteam@shamrocktechnologies.com.

For **more** information about Shamrock's other products or capabilities please visit us at our website, ShamrockTechnologies.com.

Corporate Headquarters

Foot of Pacific Street
Newark, NJ 07114
Phone: +1(800)349-1822

Henderson, KY

301 Community Drive
Henderson, KY 42420
Phone: +1(800)349-1822

Tongeren, Belgium

Heesterveldweg 21,
B-3700 Tongeren Belgium
Phone: +32 1245 8330

Tianjin, China

Fty 5, Ave. 9, TEDA
Phone: +86 22 5981 3085

The information contained in this technical data sheet is, to the best of our knowledge, true and accurate. No warranty, express or implied, is made regarding the accuracy of the information contained herein, or that results obtained from the use thereof will not infringe upon third party intellectual property rights.

Current Issue Date: 20-Aug-2015