

MicroFLON[®] S-203-RC

Micronized Polytetrafluoroethylene Powder

Product Description:




MicroFLON[®] S-203-RC powders is a micronized polytetrafluoroethylene (PTFE) powders and produced to be in compliance with EU regulatory requirements.

Application:





MicroFLON[®] S-203-RC powders are designed for thermoplastics and elastomers to reduce friction and enhance anti-wear properties. They are manufactured from prime PTFE and offer high thermal stability and are ideal for polyphenylene sulfide, polyimide, polyether ether ketone, and other high temperature applications.

MicroFLON[®] S-203-RC powders can be compounded into polyesters, polyamides, polyacetals, polycarbonates, and other engineering plastics and their blends. Addition of 5 – 25% of total formula weight PTFE provides excellent lubricity and anti-wear properties.

Features and Benefits:

-  Friction Reduction
-  Wear Resistance
-  Improved Stick-Slip Response

Typical Properties:

	Particle Size Mean Value:	15 - 25 μ m
	Bulk Density:	300 - 500 g/l
	Melting Point:	328 °C
	Specific Gravity:	2.15 - 2.20

Regulatory Status:

The components of this product are listed on multiple chemical inventories. For specific information on the applicable chemical inventories, please refer to the product SDS. This product complies with the Commission Delegated Regulation (EU) 2020/784 amending Annex I to POPs Regulation (EU) 2019/1021 (per Shamrock QSOP-202E).

Safety, Shipping and Handling:

For complete safety, shipping and handling information, please refer to the product SDS, contact your regional Customer Service Representative, or contact our Customer Service Team by e-mail at customerserviceteam@shamrocktechnologies.com.

For more information about Shamrock's other products, please visit us at our website, ShamrockTechnologies.com.

Corporate Headquarters
Foot of Pacific Street
Newark, NJ 07114
Phone: +1(800)349-1822

Henderson, KY
301 Community Drive
Henderson, KY 42420
Phone: +1(800)349-1822

Tongeren, Belgium
Heersterveldweg 21,
B-3700 Tongeren Belgium
Phone: +32 1245 8330

Tianjin, China
Fty 5, Ave. 9, TEDA
Phone: +86 22 5981 3085

The information contained in this document is, to the best of our knowledge, true and accurate. Although every effort is made to provide complete and accurate information, neither Shamrock nor any of its affiliates makes any representation, express or implied, regarding the accuracy of the data, the results to be obtained from the use thereof, and assumes no liability or responsibility for any errors or omissions, or that any such use will not infringe any patent. This information is being provided to you to assist with the evaluation of the materials described herein, and should not be relied upon without verification by you.

Issue Date: 07/08/2020