

FluoroPURE® Fiber 10C-RC

PTFE Microfiber Powder







Product Description:

FluoroPURE® Fiber 10C-RC is a polytetrafluoroethylene microfiber powder. It is produced by a unique microfiber technology. This product is produced to be in compliance with EU regulatory requirements.







Application:

The microfibers of FluoroPURE® Fiber 10C-RC have an elegant feel and incredible softness. They have a unique ability to entrap oil. They have FluoroPURE® Fiber 10C-RC is extremely flexible and can be used in mascara, hair and all silken cosmetic applications. It also can be incorporated into make-up to allow the true colors to come through in a natural fashion.

Features and Benefits:

-  Provides Softness, Flexibility, and Opacity
-  Provides High Lubricity and Uniformity
-  Provides a Higher Oil Absorption Thickens, Lengthens, and Strengthens Lashes in Mascara
-  Enhances Wear and Water Resistance
-  Achieves a Subtle Gloss Finish
-  Hides Lines and Wrinkles in Sculpturing Products

Typical Properties:

	Appearance	White Free-Flowing Fiber Powder
	Fiber Size Range:	30 – 75 microns
	Specific Gravity:	2.15 g/cm ³
	Bulk Density:	100 – 300 (g/cm ³)
	DSC Melting Point:	327 °C
	Particle Shape:	Irregular Fibers

INCI Name: Polytetrafluoroethylene

Regulatory Status

The components of this product are listed on multiple chemical inventories. For specific information on the applicable chemical inventories, please refer to the product SDS. This product complies with the Commission Delegated Regulation (EU) 2020/784 amending Annex I to POPs Regulation (EU) 2019/1021 (per Shamrock QSOP-202E).

Safety, Shipping and Handling

For complete shipping, handling, health and safety information please contact your regional Customer Service Representative. Please contact them at your convenience for instructions and Material Safety Data Sheets, the contact information is located below.

Corporate Headquarters
Foot of Pacific Street
Newark, NJ 07114
Phone: +1(800)349-1822

Henderson, KY
301 Community Drive
Henderson, KY 42420
Phone: +1(800)349-1822

Tongeren, Belgium
Heersterveldweg 21,
B-3700 Tongeren Belgium
Phone: +32 1245 8330

Tianjin, China
Fty 5, Ave. 9, TEDA
Phone: +86 22 5981 3085

The information contained in this document is, to the best of our knowledge, true and accurate. Although every effort is made to provide complete and accurate information, neither Shamrock nor any of its affiliates makes any representation, express or implied, regarding the accuracy of the data, the results to be obtained from the use thereof, and assumes no liability or responsibility for any errors or omissions, or that any such use will not infringe any patent. This information is being provided to you to assist with the evaluation of the materials described herein, and should not be relied upon without verification by you.

Issue Date: 07/08/2020