

HydroCER[®] AE-35FG

Aqueous Oxidized HDPE Emulsion

Product Description:

HydroCER[®] AE-35FG is an oxidized high-density polyethylene wax emulsion







Application:

HydroCER[®] AE-35FG is recommended for aqueous coatings, printing inks, leather coatings, seed coatings and food packaging where rub resistance and scratch resistance are required. The HydroCER[®] AE-35FG is formulated for superior gloss and to have a lower viscosity than standard food grade polyethylene emulsions.








Recommended Levels:

1-6% by weight of total formulation

Features and Benefits:

-  Slip (Low COF)
-  Abrasion Resistance
-  Clarity
-  Scratch Resistance
-  Rub Resistance
-  Sheen Stability

Typical Properties:

 Non-Volatile:	35%
 Melting Point (Wax) :	270°F/132°C
 Viscosity:	<500 cps
 pH:	9 – 10.5
 Carrier:	Water
 Density:	8.3 – 8.5 lbs/gal
 Ionic Nature:	Non-ionic

Regulatory Status:

The components of this product are listed on multiple chemical inventories. For specific information on the applicable chemical inventories, please refer to the product SDS.

21 CFR Applications: 175.105, 175.300*, 175,320*, 176.170, 176.180

Safety, Shipping and Handling:

For complete safety, shipping and handling information, please refer to the product SDS, contact your regional Customer Service Representative, or contact our Customer Service Team by e-mail at customerserviceteam@shamrocktechnologies.com.

Precautions: Keep From Freezing. Mix Well Prior To Use.

Corporate Headquarters
Foot of Pacific Street
Newark, NJ 07114
Phone: +1(800)349-1822

Henderson, KY
301 Community Drive
Henderson, KY 42420
Phone: +1(800)349-1822

Tongeren, Belgium
Heersterveldweg 21,
B-3700 Tongeren Belgium
Phone: +32 1245 8330

Tianjin, China
Fty 5, Ave. 9, TEDA
Phone: +86 22 5981 3085

The information contained in this document is, to the best of our knowledge, true and accurate. Although every effort is made to provide complete and accurate information, neither Shamrock nor any of its affiliates makes any representation, express or implied, regarding the accuracy of the data, the results to be obtained from the use thereof, and assumes no liability or responsibility for any errors or omissions, or that any such use will not infringe any patent. This information is being provided to you to assist with the evaluation of the materials described herein, and should not be relied upon without verification by you.

Issue Date: 2/20/2026