

## SuperTABER 5509-N1RC

PTFE and Polyethylene Waxes

### Product Description:

SuperTABER 5509-N1RC is a combination of polytetrafluoroethylene and a range of polyethylene waxes. SuperTABER 5509-N1RC is produced to be in compliance with REACH regulatory requirements.

### Application:









A unique combination of complementary waxes, SuperTABER 5509-N1RC increases the surface slip of the coating while imparting excellent abrasion resistance. As such, it is especially effective for reducing initial wear and provides excellent resistance to taber abrasion, falling sand abrasion and can slide wear. Coatings: Industrial, wood and powder coatings, particularly those with poor slip properties.

SuperTABER 5509-N1RC can be easily incorporated into coatings by simple stirring. However, the use of high speed mixing and dispersion equipment will not adversely affect the intercoat adhesion or physical characteristics of the coating.

### Recommended Level:

1.0 to 3.0% of the total formula weight

### Typical Properties:

	Appearance:	Off White Powder
	Specific Gravity:	1.1 g/cm <sup>3</sup>
	Particle Size Mean Value:	4.0 – 6.0 µm
	99% of Particle Under:	15.0 µm
	NPIRI Grind:	2.5 Max
	Hegman Grind:	6.5 – 7.0 Min
	DSC Melting Point:	257 – 125 °F / °C
	DSC 2 <sup>nd</sup> Melting Point:	608 / 320 °F / °C

### Regulatory Status

The components of this product are listed on multiple chemical inventories. For specific information on the applicable chemical inventories, please refer to the product SDS. This product complies with the Commission Delegated Regulation adopted on April 8th 2020 amending Annex I to POPs Regulation (EU) 2019/1021 taking effect on July 4th 2020 (per Shamrock QSOP-202E).

### Safety, Shipping and Handling

For complete shipping, handling, health and safety information please contact your regional Customer Service Representative. Please contact them at your convenience for instructions and Material Safety Data Sheets, the contact information is located below.

**Corporate Headquarters**  
Foot of Pacific Street  
Newark, NJ 07114  
Phone: +1(800)349-1822

**Henderson, KY**  
301 Community Drive  
Henderson, KY 42420  
Phone: +1(800)349-1822

**Tongeren, Belgium**  
Heersterveldweg 21,  
B-3700 Tongeren Belgium  
Phone: +32 1245 8330

**Tianjin, China**  
Fty 5, Ave. 9, TEDA  
Phone: +86 22 5981 3085