

TaberPLUS 75

Hard Bio-based wax alloy

Shamrock's product line of micronized waxes is primarily designed to provide rub and abrasion resistance.

Product Description:

TaberPlus 75 is a hard bio-based wax alloy that has components showing melting peaks ranging from 125 – 128°C.







Application:

TaberPlus 75 is used in both air dry and baked coatings for solvent and aqueous systems at 1-3% of total formula weight.

Features and Benefits:

-  Abrasion Resistance
-  Mar/Scuff

Typical Properties:

 Appearance:	White Wax Powder
 Specific Gravity:	0.98 g/cm ³
 Particle Size Mean Value:	5 µm
 99% of Particle Under:	22 µm
 NPIRI Grind:	2.5 Max
 Hegman Grind:	6.0 Min

Regulatory Status:

The components of this product are listed on multiple chemical inventories. For specific information on the applicable chemical inventories, please refer to the product SDS.

Safety, Shipping and Handling:

For complete safety, shipping and handling information please contact your regional Customer Service Representative, or our Customer Service Team at customerserviceteam@shamrocktechnologies.com.

For **more** information about Shamrock's other products or capabilities please visit us at our website, ShamrockTechnologies.com.

Corporate Headquarters
Foot of Pacific Street
Newark, NJ 07114
Phone: +1(800)349-1822

Henderson, KY
301 Community Drive
Henderson, KY 42420
Phone: +1(800)349-1822

Tongeren, Belgium
Heersterveldweg 21,
B-3700 Tongeren Belgium
Phone: +32 1245 8330

Tianjin, China
Fty 5, Ave. 9, TEDA
Phone: +86 22 5981 3085

The information contained in this document is, to the best of our knowledge, true and accurate. Although every effort is made to provide complete and accurate information, neither Shamrock nor any of its affiliates makes any representation, express or implied, regarding the accuracy of the data, the results to be obtained from the use thereof, and assumes no liability or responsibility for any errors or omissions, or that any such use will not infringe any patent. This information is being provided to you to assist with the evaluation of the materials described herein, and should not be relied upon without verification by you.

Issue Date: 2/20/2026