

AquaFLON[®] 178G-RC

PTFE/Wax Aqueous Dispersion

The AquaFLON[®] product line is comprised of aqueous dispersions of PTFE or PTFE with wax. These products are designed for stability, pourability and easy incorporation into water based systems. They are used as additives to provide slip and abrasion resistance.



Product Description:

AquaFLON[®] 178G-RC is an aqueous dispersion of a blend of a synthetic wax and polytetrafluoroethylene (PTFE) and is produced to be in compliance with EU regulatory requirements.


Application:

AquaFLON[®] 178G-RC is recommended for water-based inks and coatings. AquaFLON[®] 178G-RC is recommended for both clear and pigmented compositions at 1-5% of the total formula weight.

Features and Benefits:

-  Rub Resistance
-  Slip (Low COF)

Typical Properties:

 Hegman Grind:	6.5 Min
 Weight/Gallon:	9.4 - 9.8 Lbs / Gal
 % Solids:	50 - 54
 pH:	8 – 10
 Viscosity:	3000 – 6000 cPs

Regulatory Status:

The components of this product are listed on multiple chemical inventories. For specific information on the applicable chemical inventories, please refer to the product SDS. This product complies with the Commission Delegated Regulation (EU) 2020/784 on PFOA and (EU) 2021/1297 on C9-C14 (per Shamrock QSOP-202E and QSOP-205E).

Safety, Shipping and Handling:

Precaution: **KEEP FROM FREEZING, MIX WELL PRIOR TO USE.**

For complete safety, shipping and handling information, please refer to the product SDS, contact your regional Customer Service Representative, or contact our Customer Service Team by e-mail at customerserviceteam@shamrocktechnologies.com.

For more information about Shamrock's other products, please visit us at our website, ShamrockTechnologies.com.

Corporate Headquarters
Foot of Pacific Street
Newark, NJ 07114
Phone: +1(800)349-1822

Henderson, KY
301 Community Drive
Henderson, KY 42420
Phone: +1(800)349-1822

Tongeren, Belgium
Heersterveldweg 21,
B-3700 Tongeren Belgium
Phone: +32 1245 8330

Tianjin, China
Fty 5, Ave. 9, TEDA
Phone: +86 22 5981 3085