

FluoroSLIP® 731MG-RC

Synthetic Wax/PTFE Blend





Description:

FluoroSLIP® 731MG-RC is a blend of high melting synthetic wax, carnauba wax, and PTFE and is produced to be in compliance with EU regulatory requirements.







Application:

FluoroSLIP® 731MG-RC is developed as a performance additive to enhance surface properties in inks and coatings. It is recommended for use in thin film liquid formulations, including water-based, solvent-based, and UV inks and coatings systems. It shows exceptional performance in can coatings. Addition of 1 – 5% of total formula weight of FluoroSLIP® 731MG-RC provides excellent lubricity and abrasion resistance. FluoroSLIP® 731MG-RC is readily mixed into ink and coating formulations using standard high speed dispersion equipment.

Features and Benefits:

-  Slip (Low COF)
-  High Rub Resistance
-  Mar and Taber Abrasion Resistance
-  High Clarity and Gloss Retention

Typical Properties:

 Specific Gravity:	1.1
 Particle Size Mean Value:	3-6 µm
 99% of Particles Under:	16 µm
 NPIRI Grind:	2.0 Max
 Hegman Grind:	6.5 Min
 DSC Melting Point:	232 °F / 111 °C

Regulatory Status:

The components of this product are listed on multiple chemical inventories. For specific information on the applicable chemical inventories, please refer to the product SDS. This product complies with the Commission Delegated Regulation (EU) 2020/784 on PFOA and (EU) 2021/1297 on C9-C14 (per Shamrock QSOP-202E and QSOP-205E).

Safety, Shipping and Handling:

For complete safety, shipping and handling information, please refer to the product SDS, contact your regional Customer Service Representative, or contact our Customer Service Team by e-mail at customerserviceteam@shamrocktechnologies.com.

Corporate Headquarters
Foot of Pacific Street
Newark, NJ 07114
Phone: +1(800)349-1822

Henderson, KY
301 Community Drive
Henderson, KY 42420
Phone: +1(800)349-1822

Tongeren, Belgium
Heersterveldweg 21,
B-3700 Tongeren Belgium
Phone: +32 1245 8330

Tianjin, China
Fty 5, Ave. 9, TEDA
Phone: +86 22 5981 3085