

HydroCER[®] AE-25FG

Aqueous HDPE Emulsion (Direct Food Contact Wax Emulsion)

Product Description:

HydroCER[®] AE-25FG is a non-ionic high-density synthetic wax emulsion








Application:

HydroCER[®] AE-25FG is recommended for aqueous coatings, printing inks, leather coatings, seed coatings and food packaging where rub resistance and scratch resistance are required. The HydroCER[®] AE-25FG is formulated for superior gloss and to have a lower viscosity than standard food grade polyethylene emulsions.

Recommended Levels:

1-6% by weight of total formulation

Typical Properties:

 Non-Volatile:	25%
 Melting Point (Wax)	266°F
 Viscosity:	<500 cps
 pH value:	9 – 10.5
 Carrier:	Water
 Density:	8.3 – 8.5 lbs./gal
 Ionic Nature	Non-ionic/anionic

Regulatory Status:

The components of this product are listed on multiple chemical inventories. For specific information on the applicable chemical inventories, please refer to the product SDS.

21 CFR Applications: 175.105, 175.300*, 175,320*, 176.170, 176.180

Safety, Shipping and Handling:

For complete safety, shipping and handling information, please refer to the product SDS, contact your regional Customer Service Representative, or contact our Customer Service Team by e-mail at customerserviceteam@shamrocktechnologies.com.

Precautions: **Keep From Freezing. Mix Well Prior To Use.**

*For use with food types IV-A, V.VII(Table1) Subject to restrictions listed in (table 2). It is the responsibility of our customer to that the use of this product is safe, lawful and suitable for their application

Corporate Headquarters
Foot of Pacific Street
Newark, NJ 07114
Phone: +1(800)349-1822

Henderson, KY
301 Community Drive
Henderson, KY 42420
Phone: +1(800)349-1822

Tongeren, Belgium
Heersterveldweg 21,
B-3700 Tongeren Belgium
Phone: +32 1245 8330

Tianjin, China
Fty 5, Ave. 9, TEDA
Phone: +86 22 5981 3085

The information contained in this document is, to the best of our knowledge, true and accurate. Although every effort is made to provide complete and accurate information, neither Shamrock nor any of its affiliates makes any representation, express or implied, regarding the accuracy of the data, the results to be obtained from the use thereof, and assumes no liability or responsibility for any errors or omissions, or that any such use will not infringe any patent. This information is being provided to you to assist with the evaluation of the materials described herein, and should not be relied upon without verification by you.

Issue Date: 2/20/2026