

S-394 MG

Polyethylene Wax Powder

Product Description:

S-394 MG is a fine particle size, polyethylene wax powder.

Application:

S-394 MG provides excellent rub/abrasion resistance to liquid inks, paste inks and thin-film coatings. It has a high onset of melting, which leads to insolubility and, in inks, excellent imprintability and freedom from overprint varnish "crawling."





Recommended Level:

1.0 – 2.0% of total formula weight for liquid inks
2.0 - 3.0% for paste inks and coatings








(Too much S-394 MG will cause gloss reduction.)

Features and Benefits:

As part of the S-Series waxes, S-394 MG also features:

-  Excellent Recoatability
-  Consistently Narrow Particle Size Distribution
-  Compatibility With PTFE (0.5 – 1.0% SST-4 with 2 - 2.5% S-394 MG Recommended For Enhanced Rub Resistance)
-  Easy Dispersion With Mild Agitation (or High Speed Mixing Equipment)

Typical Properties:

 Appearance:	Off White Powder
 Specific Gravity:	0.95 g/cm ³
 Particle Size Mean Value:	3 – 4 μm
 99% of Particle under:	12 μm
 NPIRI Grind:	2.0 Max
 Hegman Grind:	6.75 Min
 DSC Melting Point:	235°F / 113°C

Regulatory Status

The components of this product are listed on multiple chemical inventories. For specific information on the applicable chemical inventories, please refer to the product SDS.

Safety, Shipping and Handling

For complete shipping, handling, health and safety information please contact your regional Customer Service Representative. Please contact them at your convenience for instructions and Material Safety Data Sheets, the contact information is located below.

Corporate Headquarters
Foot of Pacific Street
Newark, NJ 17114
Phone: +1(800)349-1822

Henderson, KY
301 Community Drive
Henderson, KY 42420
Phone: +1(800)349-1822

Tongeren, Belgium
Heersterveldweg 21,
B-3700 Tongeren Belgium
Phone: +32 1245 8330

Tianjin, China
Fty 5, Ave. 9, TEDA
Phone: +86 22 5981 3085