

## MaxWAX® 12

Oxidized Polyethylene Wax

### Product Description:

MaxWAX® 12 is a micronized high density oxidized polyethylene wax.






### Application:

MaxWAX® 12 is easily dispersible in water-based systems with moderate mixing to avoid foam generation. MaxWAX® 12 imparts good rub and slip in water based flexographic and gravure inks and coatings. With its high melting profile, it is suitable for use in aqueous coil and general industrial coatings to provide superior scuff and burnish resistance, increased abrasion performance and anti-blocking characteristics. It is also used in the coatings on crown caps for easy release.

### Recommended Level:

Inks/Coatings: 1 - 3% of the total formula weight

### Typical Properties:

|   |                     |
|---|---------------------|
|  Appearance:                 | Free Flowing Powder |
|  Specific Gravity:          | 0.96-0.99           |
|  Particle Size Mean Value: | 10 – 14 µm          |
|  DSC Melting Point:        | 130 - 133 °C        |
|  Acid Number:              | 26 – 40 mg KOH/g    |

### Regulatory Status

The components of this product are listed on multiple chemical inventories. For specific information on the applicable chemical inventories, please refer to the product SDS.

### Safety, Shipping and Handling

For complete shipping, handling, health and safety information please contact your regional Customer Service Representative. Please contact them at your convenience for instructions and Material Safety Data Sheets, the contact information is located below.

**Corporate Headquarters**  
Foot of Pacific Street  
Newark, NJ 07114  
Phone: +1(800)349-1822

**Henderson, KY**  
301 Community Drive  
Henderson, KY 42420  
Phone: +1(800)349-1822

**Tongeren, Belgium**  
Heersterveldweg 21,  
B-3700 Tongeren Belgium  
Phone: +32 1245 8330

**Tianjin, China**  
Fty 5, Ave. 9, TEDA  
Phone: +86 22 5981 3085

The information contained in this document is, to the best of our knowledge, true and accurate. Although every effort is made to provide complete and accurate information, neither Shamrock nor any of its affiliates makes any representation, express or implied, regarding the accuracy of the data, the results to be obtained from the use thereof, and assumes no liability or responsibility for any errors or omissions, or that any such use will not infringe any patent. This information is being provided to you to assist with the evaluation of the materials described herein, and should not be relied upon without verification by you.

Issue Date: 2/20/2026